Bandstrukturmethoden Demo 2: Nickel-Kristall (fcc)

Bandstrukturrechnung mittels FP-LAPW WIEN2k-02

- **Kristallstruktur von metall. Ni → fcc**
- **Input für das WIEN-Programm**
- **Vorbereitung der Bandstrukturrechung (mit weiteren wichtigen Parametern).**
- **Die selbstkonsistente Bandstrukturrechnung**
- **Ergebnisse**
- **Variation von RKMAX = Größe der LAPW-Basis**



WIEN2k: An Augmented Plane Wave Plus Orbitals Program for Calculating Crystal Properties

P. Blaha, K. Schwarz, G. Madsen, D. Kvasnicka, J. Luitz,
Inst. of Physical and Theoretical Chemistry, Vienna University of Technology

Elektronenstruktur (Z=28):

$$1s^2\ \ 2s^2\ \ 2p^6\ \ 3s^2\ \ 3p^6\ \ 3d^8\ \ 4s^2$$

oder

$$1s^2\ \ 2s^2\ \ 2p^6\ \ 3s^2\ \ 3p^6\ \ 3d^8\ \ 4s^2$$

- **Input für das WIEN-Programm: Ni_demo.struct**

```
 FCC Ni
F    LATTICE,NONEQUIV.ATOMS: 1
MODE OF CALC=NREL
 6.7000    6.7000     6.7000
ATOM=  1: X=0.00000000 Y=0.00000000 Z=0.00000000
          MULT= 1          ISPLIT= 2
Ni         NPT=  381  R0=.000050000 RMT=2.300000000  Z:28.0
LOCAL ROT MATRIX:    1.0000000 0.0000000 0.0000000
                     0.0000000 1.0000000 0.0000000
                     0.0000000 0.0000000 1.0000000
   0      NUMBER OF SYMMETRY OPERATIONS
```



Nickel-Bandstruktur: RKMAX = 7.0



Nickel-Bandstruktur: RKMAX = 5.0



Nickel-Bandstruktur: spin-polarisiert UP



Nickel-Bandstruktur: spin-polarisiert DOWN



Figure 1: Bulk copper DFT-LDA band structure (solid line), compared with photoemission data (points).
Theory: Marini et al., Phys. Rev. B **64**, 195125 (2001),
experiment: Courths and Hüfner, Phys. Rep. **112**, 53 (1984).



Figure 2: Solid line: GW results for the bulk copper band structure, compared with the DFT-LDA results (dashed line), and with experimental photoemission data.
Theory: Marini et al., Phys. Rev. Lett. **88**, 016403 (2002),
experiment: Courths and Hüfner, Phys. Rep. **112**, 53 (1984).